

(12) **United States Patent**
Wang et al.

(10) **Patent No.:** **US 9,368,710 B2**
(45) **Date of Patent:** **Jun. 14, 2016**

(54) **TRANSPARENT FLEXIBLE
NANOGENERATOR AS SELF-POWERED
SENSOR FOR TRANSPORTATION
MONITORING**

(71) Applicant: **Georgia Tech Research Corporation,**
Atlanta, GA (US)

(72) Inventors: **Zhong Lin Wang,** Atlanta, GA (US);
Youfan Hu, Atlanta, GA (US); **Long
Lin,** Atlanta, GA (US)

(73) Assignee: **Georgia Tech Research Corporation,**
Atlanta, GA (US)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 374 days.

(21) Appl. No.: **14/022,407**

(22) Filed: **Sep. 10, 2013**

(65) **Prior Publication Data**

US 2014/0007687 A1 Jan. 9, 2014

Related U.S. Application Data

(63) Continuation-in-part of application No. 13/473,867,
filed on May 17, 2012, now Pat. No. 8,829,767.

(60) Provisional application No. 61/698,854, filed on Sep.
10, 2012, provisional application No. 61/486,927,
filed on May 17, 2011, provisional application No.
61/596,405, filed on Feb. 8, 2012.

(51) **Int. Cl.**
G01P 3/02 (2006.01)
H01L 41/08 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **H01L 41/0805** (2013.01); **B82Y 15/00**
(2013.01); **B82Y 30/00** (2013.01);
(Continued)

(58) **Field of Classification Search**

CPC G01L 1/162; H01L 41/072; H02N 2/18;
F23Q 3/002

USPC 310/323.21, 339
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,554,907 A * 9/1996 Dixon G08G 1/02
310/319

6,586,095 B2 7/2003 Wang et al.

(Continued)

OTHER PUBLICATIONS

KR 10 20070052872, Gyeong-Chan Jang, Clustered piezo sensor
and traffic parameter measurement and weigh-in-motion apparatus
and method using the same.*

(Continued)

Primary Examiner — Shawki S Ismail


Assistant Examiner — Bryan Gordon

(74) *Attorney, Agent, or Firm* — Bryan W. Bockhop;
Bockhop IP Law, LLC

(57) **ABSTRACT**




A traffic sensor includes a flexible substrate having a top surface. A piezoelectric structure extends from the first electrode layer. The piezoelectric structure has a top end. An insulating layer is infused into the piezoelectric structure. A first electrode layer is disposed on top of the insulating layer. A second electrode layer is disposed below the flexible substrate. A packaging layer is disposed around the substrate, the first electrode layer, the piezoelectric structure, the insulating layer and the second electrode layer. In a method of sensing a traffic parameter, a piezoelectric nanostructure-based traffic sensor is applied to a roadway. An electrical event generated by the piezoelectric nanostructure-based traffic sensor in response to a vehicle interacting with the piezoelectric nanostructure-based traffic sensor is detected. The electrical event is correlated with the traffic parameter.

16 Claims, 5 Drawing Sheets



- (51) **Int. Cl.**
- | | | | | | |
|--------------------|-----------|--------------|------|---------|--|
| G08G 1/01 | (2006.01) | 2010/0026142 | A1 | 2/2010 | Jones et al. |
| G01G 19/08 | (2006.01) | 2010/0117488 | A1 | 5/2010 | Wang et al. |
| B82Y 15/00 | (2011.01) | 2010/0139750 | A1 | 6/2010 | Kim et al. |
| B82Y 30/00 | (2011.01) | 2010/0141095 | A1 | 6/2010 | Park |
| H01L 27/20 | (2006.01) | 2010/0147371 | A1 | 6/2010 | Cho |
| H01L 41/319 | (2013.01) | 2010/0171095 | A1 | 7/2010 | Wang et al. |
| H02N 2/18 | (2006.01) | 2010/0191153 | A1 | 7/2010 | Sanders et al. |
| H01L 41/113 | (2006.01) | 2010/0253184 | A1 * | 10/2010 | Choi H02N 2/18
310/339 |
| H01L 41/18 | (2006.01) | 2010/0258160 | A1 | 10/2010 | Wang et al. |
| B82Y 40/00 | (2011.01) | 2010/0314968 | A1 | 12/2010 | Mohamadi |
| | | 2011/0012479 | A1 * | 1/2011 | Nakamura B60C 23/0411
310/339 |
| | | 2011/0050042 | A1 * | 3/2011 | Choi H01L 41/314
310/339 |
| | | 2011/0107569 | A1 | 5/2011 | Wang et al. |
| | | 2012/0293047 | A1 * | 11/2012 | Wang H01L 27/20
310/339 |
- (52) **U.S. Cl.**
- CPC **G01G 19/08** (2013.01); **G01P 3/02** (2013.01); **G08G 1/0104** (2013.01); **H01L 27/20** (2013.01); **H01L 41/082** (2013.01); **H01L 41/1136** (2013.01); **H01L 41/183** (2013.01); **H01L 41/319** (2013.01); **H02N 2/18** (2013.01); **H02N 2/181** (2013.01); **H02N 2/186** (2013.01); **B82Y 40/00** (2013.01); **Y10S 977/948** (2013.01)
- (56) **References Cited**
- U.S. PATENT DOCUMENTS
- | | | | |
|--------------|------|---------|--------------------------------------|
| 7,220,310 | B2 | 5/2007 | Wang et al. |
| 7,351,607 | B2 | 4/2008 | Wang et al. |
| 7,705,523 | B2 | 4/2010 | Wang et al. |
| 7,898,156 | B2 | 3/2011 | Wang et al. |
| 8,039,834 | B2 | 10/2011 | Wang et al. |
| 2003/0205657 | A1 | 11/2003 | Voisin |
| 2004/0127025 | A1 | 7/2004 | Crocker, Jr. et al. |
| 2005/0127677 | A1 * | 6/2005 | Luttrull H02N 2/18
290/1 R |
| 2005/0188751 | A1 | 9/2005 | Puskas |
| 2005/0242366 | A1 | 11/2005 | Parikh et al. |
| 2008/0067618 | A1 | 3/2008 | Wang et al. |
| 2008/0265346 | A1 * | 10/2008 | Kimino G01P 15/0802
257/417 |
| 2009/0066195 | A1 | 3/2009 | Wang et al. |
| 2009/0115293 | A1 | 5/2009 | Wang et al. |
| 2009/0179523 | A1 | 7/2009 | Wang et al. |
| 2009/0209303 | A1 | 8/2009 | Kroll et al. |
- OTHER PUBLICATIONS
- Jeon et al., "MEMS power generator with transverse mode thin film PCT," Science Direct, vol. 122, Issue 1, Jul. 29, 2005, pp. 16-22.
- Gao et al., Nanoarchitectures of semiconducting and piezoelectric zinc oxide, J. Applied Physics 97, 044304 (2005).
- Wang et al., "Large-Size Lifiable Inverted-Nanobowl Sheets as Reusable Masks for Nanolithography," Nano Letters, vol. 5, No. 9, 2005, 1748-1788.
- Lao et al., "Formation of double-side teathed nanocombs of ZnO and self-catalysis of Zn-terminated polar surface," Chemical Physics Letters, Elsevier B.V., 2005.
- Jeon et al., "MEMS power generator with transverse mode thin film PZT," Sensors and Actuators A Physical, Elsevier, (2005).
- Lao et al., "Formation of double-side teathed nanocombs of ZnO and self-catalysis of Zn-terminated polar surface," Chemical Physics Letters (Science Direct), (Abstract), 2007.
- Wang et al., "Large-Size Lifiable Inverted-Nanobowl Sheets as REusable Masks for Nanolithography," Nano Letters, vol. 5, (Abstract), 2005.
- Wang et al., "Piezoelectric Nanogenerators Based on Zinc Oxide Nanowire Arrays," Science, vol. 312, pp. 242-245, Apr. 14, 2006.
- Wang et al., "An aqueous solution-based doping strategy for large-scale synthesis of Sb-doped ZnO nanowires," Nanotechnology, vol. 22, pp. 1-8, Apr. 1, 2011.

* cited by examiner






FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E




FIG. 2F




FIG. 2G




FIG. 2H




FIG. 2I




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10

1

TRANSPARENT FLEXIBLE NANOGENERATOR AS SELF-POWERED SENSOR FOR TRANSPORTATION MONITORING

CROSS-REFERENCE TO RELATED APPLICATION(S)

This application claims the benefit of U.S. Provisional Patent Application Ser. No. 61/698,854, filed Sep. 10, 2012, the entirety of which is hereby incorporated herein by reference.

This application is a continuation-in-part of, and claims the benefit of, U.S. patent application Ser. No. 13/473,867, filed May 17, 2012, which claims the benefit of U.S. Provisional Patent Application Ser. No. 61/486,927, filed May 17, 2011, and U.S. Provisional Patent Application Ser. No. 61/596,405, filed Feb. 8, 2013, the entirety of each of which is hereby incorporated herein by reference.

STATEMENT OF GOVERNMENT INTEREST

This invention was made with government support under agreement No. DE-FG02-07ER46394, awarded by the Department of Energy. The government has certain rights in the invention.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to power generators and, more specifically, to a power generator for monitoring vehicles.

2. Description of the Related Art

Nanoscale and microscale devices are being in such diverse applications as sensors, transducers, data processors, control systems, communications systems and many more. Virtually all of these applications require a power source. While most nanoscale and microscale devices do not consume very much power, the wiring difficulties associated with such systems can be too cumbersome when conventional power sources are employed.

There are many portable macro-scale devices for which conventional power systems are either too cumbersome or add undesirable weight. For example, Bluetooth headsets typically consume about several microwatts (when the data transmission rate is about 500 kbits/s, the power consumption is about 10 nW/bit). In some applications it is desirable to drive such devices by scavenging energy from the sources in the environment such as gentle airflow, vibration, sonic wave, solar, chemical, or thermal energy.

Neuroprosthetics have been developed to restore motor, sensory, and cognitive functions in patients having nerve injuries or diseases by functional electrical stimulation (FES). A broad range of neuroprostheses have been developed and even commercialized to target specific needs, including pain relief, visual/auditory recovery, bladder management, and treatment for neurological disorders such as Alzheimer's disease and Parkinson's disease. Essentially, FES utilizes short bursts of electrical impulses to muscle or neural tissue. The necessary electric energy may be supplied by such technologies as on-board batteries or external energy inputs in forms of external AC power, electromagnetic generators, laser irradiation, etc. However, none of the developed neuroprostheses currently harness energy sources that are readily available within a biosystem. Harvesting ambient energy in biosystems, especially biomechanical energy that

2

abundantly exists in a human body, could allow self-powered neuroprostheses to operate independently and sustainably.

Traffic sensors are used in a variety of applications, including traffic counting, speed detection and vehicle weight measurement. Some sensors are used for gathering traffic statistics and some are used in traffic law enforcement. Conventions systems employ such devices as magnetic induction detection and pressure change detection. Such conventional systems are not self powering and usually require an external power source, such as a battery, a generator or solar panels to operate. Such power sources add bulk and cost to traffic sensors.

Therefore, there is a need for a self-powered traffic sensor.

SUMMARY OF THE INVENTION

The disadvantages of the prior art are overcome by the present invention which, in one aspect, is a generator that includes a substrate, a first electrode layer, a piezoelectric structure, an insulating layer and a second electrode layer. The substrate has a top surface and the first electrode layer is disposed on the top surface of the substrate. The piezoelectric structure extends from the first electrode layer. The piezoelectric structure has a top end. The insulating layer is disposed on the top end of the piezoelectric structure. The second electrode layer is disposed on the non-conductive layer and is spaced apart from the piezoelectric structure.

In another aspect, the invention is a method of making a generator, in which a first electrode layer is applied to a top surface of a substrate. A seed layer is deposited onto the first electrode layer. A dense plurality of vertically-aligned piezoelectric elongated nanostructures is grown from the seed layer. Each nanostructure has a top end. An insulating layer is deposited onto the top ends of the nanostructures. A second electrode layer is deposited onto the insulating layer so that the nanostructures are electrically isolated from the second electrode layer.

In yet another aspect, the invention is a method of making a piezoelectric nanogenerator, in which a first electrode layer is applied to a surface of substrate. A nanostructure seed layer is applied to the first electrode layer. A mask is applied to the nanostructure seed layer. The mask defines a plurality of spaced-apart openings therethrough that expose selected areas of the nanostructure seed layer. A plurality nanostructures is grown from the nanostructure seed layer through the openings. The mask is removed. An insulator layer is applied to the nanostructures. A second electrode layer is deposited onto the insulator layer so that the second electrode layer is electrically isolated from the nanostructures and so that when the nanostructures are deformed by a force, the nanostructures piezoelectrically induce an electrical field that influences the second electrode layer.

In another aspect, the invention is a traffic sensor that includes a flexible substrate having a top surface. A piezoelectric structure extends from the first electrode layer. The piezoelectric structure has a top end. An insulating layer is infused into the piezoelectric structure. A first electrode layer is disposed on top of the insulating layer. A second electrode layer is disposed below the flexible substrate. A packaging layer is disposed around the substrate, the first electrode layer, the piezoelectric structure, the insulating layer and the second electrode layer.

In yet another aspect, the invention is a method of sensing a traffic parameter, in which a piezoelectric nanostructure-based traffic sensor is applied to a roadway. An electrical event generated by the piezoelectric nanostructure-based traffic sensor in response to a vehicle interacting with the

piezoelectric nanostructure-based traffic sensor is detected. The electrical event is correlated with the traffic parameter.

These and other aspects of the invention will become apparent from the following description of the preferred embodiments taken in conjunction with the following drawings. As would be obvious to one skilled in the art, many variations and modifications of the invention may be effected without departing from the spirit and scope of the novel concepts of the disclosure.

BRIEF DESCRIPTION OF THE FIGURES OF THE DRAWINGS

FIGS. 1A-1F are a series of schematic drawings showing a first method of making a nanogenerator.

FIGS. 2A-2I are a series of schematic drawings showing a second method of making a nanogenerator.

FIG. 3 is a micrograph of a nanogenerator made according to the method shown in FIGS. 1A-1F.

FIG. 4 is an elevational schematic view of an embodiment of a self-powered sensor.

FIG. 5 is a schematic view of one embodiment of a self-powered sensor in use.

FIG. 6 is a graph relating voltage to time relative to the embodiment in FIG. 5.

FIG. 7 is a schematic view of a two sensor embodiment in use.

FIG. 8 is a graph relating voltage to time relative to the embodiment in FIG. 7.

FIG. 9 is a schematic view of a weight sensor embodiment in use.

FIG. 10 is a graph relating voltage to time relative to the embodiment in FIG. 9.

DETAILED DESCRIPTION OF THE INVENTION

A preferred embodiment of the invention is now described in detail. Referring to the drawings, like numbers indicate like parts throughout the views. Unless otherwise specifically indicated in the disclosure that follows, the drawings are not necessarily drawn to scale. As used in the description herein and throughout the claims, the following terms take the meanings explicitly associated herein, unless the context clearly dictates otherwise: the meaning of “a,” “an,” and “the” includes plural reference, the meaning of “in” includes “in” and “on.”

The following patents, issued to Wang et al., disclose methods of making piezoelectric nanostructures and are incorporated herein by reference for the purpose of disclosing piezoelectric nanostructure growth methods: U.S. Pat. No. 7,351,607, issued on Apr. 1, 2008; U.S. Pat. No. 7,982,370, issued on Jul. 19, 2011; U.S. Pat. No. 7,898,156, issued on Mar. 1, 2011; and U.S. Pat. No. 8,039,834 issued on Oct. 18, 2011. The following patent applications, filed by Wang et al., disclose methods of making piezoelectric nanostructures and are incorporated herein by reference for the purpose of disclosing piezoelectric nanostructure growth methods: Ser. No. 13/091,855, filed on Apr. 21, 2011 and Ser. No. 13/473,867 filed May 17, 2012.

As shown in FIGS. 1A-1F, in one method of making a nanogenerator **100** a conductive adhesion layer **112** is deposited onto a substrate **110**. The substrate **110** could be a rigid substrate, such as a silicon crystal, or it could be a flexible substrate, such as a polydimethylsiloxane (PDMS) layer or a polystyrene layer. The conductive adhesion layer **112**, which acts as a first electrode layer, could include a material such indium tin oxide (ITO) or a metal such as chromium. A

nanostructure seed layer **114** is sputtered, or otherwise deposited, onto the conductive adhesion layer **112**. A piezoelectric structure, which can include a piezoelectric film or a plurality of elongated piezoelectric nanostructures **116**, such as zinc oxide nanowires, is grown from the seed layer **114**. (While FIGS. 1B-1F show the nanostructures **116** being spaced apart, in one embodiment they would be densely packed.) An insulating layer **118** is deposited on the top surfaces of the nanostructures **116** and a second electrode layer **120**, such as a metal layer (e.g., chromium, silver, aluminum, etc.), is deposited on top of the insulating layer **118**. The insulating layer **118** electrically isolates the nanostructures **116** from the second electrode layer **120** so that, as shown in FIGS. 1E and 1F, when a force is applied to the nanogenerator **100** (such as in the direction of the bold arrows), the piezoelectric effect in the nanostructures **116** induces an electric field (represented by the lighter arrows) that influences the second electrode layer **120**. In one embodiment, the insulating layer **118** includes a p-type polymer, which was found to show excellent performance. If the nanogenerator **100** is coupled to an energy storage circuit **124** and a load **122**, then electrons will flow through the circuit **124** and power the load **122**.

The nanogenerator **100** employs the piezoelectric potential generated in the nanowires **116** as it is being dynamically strained under an extremely small force. A transient flow of electrons in an external load as driven by the piezopotential to balance the Fermi levels at the two contacts is the fundamental mechanism of the nanogenerator **100**. The power generated by a nanogenerator **100** may not be sufficient to continuously drive a device, but an accumulation of charges generated over a period of time is sufficient to drive the device to work for a few seconds. This is very suitable for applications in the fields of sensing, infrastructure monitoring and sensor networks. A common characteristic for these applications is that there are so many sensors in the system, and each sensor is expected to work independently and wirelessly, but all of them may be linked through a network/internet. Each sensor is not required to work continuously and simultaneously, instead, it will have a “blinking” working mode with a standby status and active status. The standby mode is normally longer, while the active mode is shorter. The energy scavenged and stored during the standby status can be used to drive it in the active mode. This means that these sensors periodically sample from their working environment and transmit data within a fraction of second. The nanogenerator **100** can be used to harvest energy from the environment and store most of the energy when the sensor is in the standby mode. Then the collected energy will be used to trigger the sensor, process and transmit the data in the active mode.

In one experimental embodiment, the power source in this includes the energy harvesting and storage modules. The harvester scavenges some kind of energy (solar, thermal, mechanical and/or chemical) from the environment and stores it in the energy storage module. Thus the collected power is used to drive the other parts of the system. The sensors detect the changes in the environment, while the data processor & controller analyze the information. Then, the signal is sent out by the data transmitter, and simultaneously the response is received. This embodiment is made of a nanogenerator for harvesting mechanical energy, a low-loss full-wave bridge rectifier, a capacitor for storing the energy, an infrared photodetector and a wireless data transmitter.

The nanogenerator used in the integrated system employed a free-standing cantilever beam made of a five-layer structure using densely packed zinc oxide (ZnO) nanowire textured films. The nanogenerator was fabricated on a flexible polyester (PS) substrate (Dura-Lar™, 220 μm in thickness). First,

5

a 5 nm thick Cr adhesion layer followed by a 50 nm thick ZnO seed layer were deposited at the selected rectangular region of 1 cm×1 cm on the top and bottom surfaces of the substrate. The ZnO seed layer is for growing densely packed ZnO nanowires via a wet chemical method. The nutrient solution used in the chemical growth process of ZnO densely packed nanowires textured films was an equal molar aqueous solution of $\text{Zn}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ and hexamethylenetetramine (HMTA), and the concentration was 0.1 M. The nanowire films at the top and bottom surfaces were grown sequentially by placing the substrate at the top of the nutrient solution with one face down. Because of the surface tension, the substrate floated on the solution surface. Growth of ZnO nanowires was carried out in a mechanical convection oven (model Yamato DKN400, Santa Clara, Calif.) at 95° C. for 5 hours. The dimensions of the nanowires were about 150 nm in diameter and 2 μm in length. The ZnO nanowires were grown vertically from the substrate, with a high packing density, and the bottoms of these nanowires were bonded through the ZnO seed layer. Tweezers were used to scratch the top surfaces of these nanowires to establish that the top surfaces of these nanowires were also bonded together tightly in a uniform film. Therefore, the entire ZnO structure could be regarded as a textured film that included fully packed ZnO nanowire arrays between two parallel ZnO films. According to the growth mechanism, the c-axes for these nanowires were their growth direction. Then, a thin layer of poly(methyl methacrylate) (PMMA) (MicroChem 950k A11) was spin coated on both surfaces of the substrate at the speed of 3000 rpm, followed by a Cr/Au layer deposition on the central rectangular area serving as the electrode of the nanogenerator. Finally, the whole device was fully packaged with polydimethylsiloxane (PDMS) to enhance the mechanical robustness and flexibility. The size of the effective working area of the nanogenerator was 1 cm×1 cm. Two leads were connected to the top and bottom electrodes, respectively. It must be pointed out that the processing temperature was below 100° C. so that the entire process is adaptable for flexible electronics.

There are two scenarios if the ZnO film is made of densely packed nanowires. When the nanogenerator is bent, considering the neutral plane of strain is at the central of the substrate the nanowire film on the stretched surface of the substrate is subject to a tensile stress, while the one on the compressed surface is under compressive stress. First, if the bonding between the nanowires is very strong to form a solid film with considering that the growth direction of the nanowires is along c-axis (polar direction for ZnO), a tensile stress perpendicular to the nanowires results in a compressive strain along the c-axis direction, thus, creating a piezopotential drop from the roots of the nanowires to their top-ends. At the same time, a corresponding compressive stress is applied to the nanowires on the bottom surface of the substrate, resulting in a tensile strain along the c-axis, thus, the top-ends of the nanowires have a higher piezopotential than their roots. Therefore, the piezopotential drops in the top and bottom ZnO films have the same polarity, and they add up constructively. This piezopotential distribution will introduce induced charges in the top and bottom electrodes, and consequently generating the output voltage.

Secondly, in a case that the bonding between the nanowires is very weak with the possibility of inter-wire sliding/gaps, no piezoelectric potential would be produced by the film on the top surface of the substrate that is under tensile stress. But, considering the nanowires are fully packed and can be squeezed between each other, a piezopotential drop is still created with some degradation by the film at the substrate bottom surface that is subject to a compressive stress. There-

6

fore, a potential drop is also expected between the top and bottom electrodes, but with its magnitude drops less than half in comparison to that in the first case. Also, it is known that the as-grown ZnO nanowires have n-type doping, which can significantly screen the higher piezopotential side, but leave the lower piezopotential side almost unchanged. Thus, the output voltage of the nanogenerator may be smaller than the theoretically calculated value due to the reasons list above.

For an experimental nanogenerator structure, there are three factors that are important to the power output performance: the length of the nanowires, the thickness of the substrate and the magnitude of the nanogenerator distortion. From the practical point of view, there are two modes to trigger the nanogenerator depending on the form of the mechanical energy scavenged by the nanogenerator s in the environment. For cases where the nanogenerator s are triggered at a constant stress, such as air flow, the calculated results show that the piezopotential between the two electrodes increases as the length of the nanowires is increased or the thickness of the substrate is decreased. When the applied strain is fixed, such as when the nanogenerator is driven by the vibrations of a bridge where the trigger source is rigid, the piezopotential changes in the opposite sense compared to the former case. Thus, by adjusting the two competing factors, the thickness of the substrate and the length of the nanowire arrays, the device can be optimized to maximize its power harvesting efficiency to specific working situations according to the character of the scavenged energy in the environment. Increasing strain can also significantly enhance the output voltage. In addition, ZnO is a biocompatible and environmentally friendly material. The nanowire films can be grown at very low temperature (<100° C.) on any kind of substrate and any shape of substrate.

Utilizing densely grown ZnO nanowire textured films grown on a polymer substrate by low temperature chemical method has been demonstrated as an effective approach for harvesting low-frequency mechanical energy. A nanogenerator with a free cantilever beam construction was fabricated that was made of a five-layer structure: a flexible polymer substrate, ZnO nanowire textured films on its top and bottom surfaces, and electrodes on the surfaces. When it was strained to 0.12% at a strain rate of 3.56% S^{-1} , the measured output voltage reached 10 V, and the output current exceeded 0.6 μA for a NG that was 1 cm^2 in size (corresponding power density 10 mW/cm^2). By storing the energy generated by the nanogenerator, we have demonstrated a self-powered system that can work independently and wirelessly. The system included a nanogenerator, rectification circuit, and capacitor for energy storage, sensor, and RF data transmitter. Wireless signals sent out by the system were detected by a commercial radio at a distance of 5-10 meters. Thus, ZnO nanowire generators are useful for building self-powered systems with capability of long distance data transmission, and have potential applications in wireless biosensing, environmental infrastructure monitoring, sensor networks, personal electronics and even national security.

As shown in FIGS. 2A-2I, one embodiment of a nanogenerator **200** allows for substantial power generation while limiting lateral charge transport between different nanostructures **216**. This embodiment employs an array of separated blocks of nanostructures **216**. This embodiment is constructed by cleaning the top surface of a substrate **210**, which in one embodiment can include PDMS, and then applying an ITO adhesion layer **212** to the clean surface of the substrate **210**. The ITO adhesion layer **212** acts as a first electrode layer. A zinc oxide seed layer **214** is applied to the adhesion layer **212** using an RF sputtering process. A mask **230**, such as a

photolithography mask, is applied to the seed layer **214**. The mask **230** defines a plurality of openings **232** therethrough that expose selected areas of the seed layer **214**. A plurality of densely packed zinc oxide nanowires **216** is grown from the exposed areas of the seed layer **214**. The nanowires **216** are disposed in separated blocks. The spaces between the blocks of nanowires prevent lateral charge transport between the blocks of nanowires **216** thereby reducing inefficiency. The mask **230** may be removed, as shown in FIG. 2F and the nanowires **216** are covered with an insulating layer **218**, such as a poly(methyl methacrylate) (PMMA) layer, as shown in FIG. 2G. A second electrode layer **220**, which could be a metal layer, is applied to the insulating layer **218** and another PMMA layer **222** is applied to envelope the entire system as a packaging layer. A pair of wires **230** are used to couple the first electrode layer **212** and the second electrode layer **220** to the loads that the nanogenerator **200** powers.

In one experimental embodiment, a pre-cleaned silicon substrate was consecutively deposited with an ITO layer and a ZnO seed layer by RF sputtering. Not only does the ITO layer play a role as a conductive electrode, but also it promotes adhesion between the ZnO seed and the substrate. Photolithography was then performed to open an array of square windows on photoresist with narrow spacing in between. The photoresist serves as a mask so that ZnO nanowires only grow on the exposed seed surface in the subsequent synthesis step by wet chemical method. Following stripping off any residual photoresist, the nanowires were thermally annealed. Then a layer of PMMA was applied cover the synthesized nanowires by spin-coating, followed by depositing a top metal electrode of aluminum. Finally, another layer of PMMA was used for packaging. Two terminal leads rested on the ITO layer and the aluminum layer for electrical measurement. The process flow is compatible with batch fabrication techniques, which allow multiple silicon wafers to be parallel processed, followed by being diced into individual devices.

The superior performance and robustness of the newly designed nanogenerator may be attributable to the PMMA layer between the nanowires and the metal electrode. Such a thin layer offers a number of advantages. First of all, it is an insulating layer that provides a potential barrier of infinite height, preventing the induced electrons in the electrodes from internal 'leaking' through the ZnO/metal interface. It replaces the Schottky contact in earlier designs. Furthermore, the PMMA fills the gap between nanowires by capillary force and forms a capping at the very top. Consequently when a force is applied along the vertical direction, the stress can be transmitted through the capping layer to all NWs under the force-applied area, greatly enhancing the nanogenerator's efficiency. It also serves as a buffer layer protecting nanowires from intimate interaction with the electrode, improving the nano generator's robustness.

It is also noteworthy that nanowires were selectively grown in photolithography-designated regions. Such segmentation is designed to optimize the nanogenerator's output. Though thermal annealing during the fabrication might help reducing the concentration of free charge carriers, there is still finite conductivity within ZnO nanowires. As a result, free charge carriers within the nanowires will partially screen the piezopotential, leading to reduced magnitude of it and thus degraded performance of the nanogenerator. The nanowires are so densely packed that they are all electrically connected in parallel. On condition that a force is applied on an area smaller than the device's dimension or the applied force has a non-uniform distribution, only the nanowires located directly beneath the force-applied area will experience strain and thus

generate piezopotential, which are referred to as active nanowires. Owing to the presence of segmentation, native free charge carriers within the nanowires that are not directly compressed under the force-applied area (referred to as inactive nanowires) are isolated from the active nanowires. Hence they will not be involved in screening, preserving the piezopotential from further degradation. However, if no segmentation is made among the nanowires, the free carriers in the inactive nanowires tend to drift toward the high piezopotential side of the active nanowires, which can lower the local piezopotential and the thus the output.

The electric output can be tremendously scaled up by linear superposition. An energy-harvesting pad was fabricated with nine NGs in parallel connection. Being punched by a human palm, the peak value of V_{oc} and I_{sc} exceeded 58 V and 134 μ A, respectively. Using such a significant output, the inventors were able to charge a capacitor of 2 μ F to over 3 V with less than 20 times of palm impact.

One embodiment of a traffic sensor **300** is shown in FIG. 4. A flexible substrate includes a layer **310** of a flexible material, such as PDMS (or one of many other flexible materials). A piezoelectric structure **312**, such as a dense plurality of vertically aligned ZnO nanowires or a piezoelectric film, is grown from the flexible layer **310** and an insulating layer **314** (which could include PMMA, Al_2O_3 , HfO_2 , an insulating polymer, or certain combinations of these materials) is infused into the piezoelectric structure. A first electrode layer **318** is disposed on top of the insulating layer and a second electrode layer **316** is disposed below the flexible substrate. Electrode layers **318** and **316** could include a conductor such as ITO (indium tin oxide), which is transparent, or a metal. A flexible packaging layer **320** (which could include PMMA) is disposed around the substrate **310**, the first electrode layer **318**, the piezoelectric structure **312**, the insulating layer **314** and the second electrode layer **316**.

In use, as shown in FIGS. 5 and 6, the piezoelectric nanostructure-based traffic sensor **300** is embedded into a roadway **10**. The weight of a vehicle **12** is applied to the traffic sensor **300** causes an electrical event in the traffic sensor **300**, such as a voltage transient **322**. As a load is applied, the piezoelectric structure **312** in the traffic sensor **300** generates a charge imbalance that can be sensed as a positive voltage transient **322**. As the load is released, the recovering piezoelectric structure **312** generates a charge imbalance of opposite polarity that can be sensed as a negative voltage transient **324**. Such voltage events can be correlated with a traffic parameter, for example, a simple count of positive voltage transients **322** can provide a count of vehicles that have passed over a selected part of the roadway **10**.

As shown in FIGS. 7 and 8, use of a first sensor **330** and a second sensor **332** on the same roadway **10** can be used to detect the speed of a vehicle **12** by determining the time between a voltage transient **334** from the first sensor **330** and the voltage transient **336** from the second sensor **332**, in which the speed is the distance d divided by the time differential Δt . This could be useful both in the context of collecting road usage statistics and in speed control applications.

In another application, as shown in FIGS. 9 and 10, the traffic sensor **300** could be used to measure a vehicle's weight. Since the output voltage **342** from the sensor **300** is proportional to the amount of force applied to the sensor **300**, the voltage **342** is proportional to the weight of the vehicle **12**. This embodiment could be useful both for gathering traffic usage statistics and in weigh stations used in carrier highway tax enforcement.

Because the device generates its own power, there is no need for a battery, a remote generator or other power source in

traffic applications. Also, in yet another embodiment, the device disclosed herein could also be used to power roadside electrical devices, such as illuminated signs, sensors and the like.

The above described embodiments, while including the preferred embodiment and the best mode of the invention known to the inventor at the time of filing, are given as illustrative examples only. It will be readily appreciated that many deviations may be made from the specific embodiments disclosed in this specification without departing from the spirit and scope of the invention. Accordingly, the scope of the invention is to be determined by the claims below rather than being limited to the specifically described embodiments above.

What is claimed is:

1. A traffic sensor, comprising:

- (a) a flexible substrate having a top surface;
- (b) a piezoelectric structure, that includes a dense plurality of vertically-aligned piezoelectric elongated nanostructures, extending from the first electrode layer, the piezoelectric structure having a top end;
- (c) an insulating layer infused into a portion of the piezoelectric structure at the top end of the piezoelectric structure;
- (d) a first electrode layer disposed below the flexible substrate;
- (e) a second electrode layer disposed on top of the insulating layer so that the insulating layer electrically isolates the second electrode layer from the top end of the piezoelectric structure; and
- (f) a packaging layer disposed around the substrate, the first electrode layer, the piezoelectric structure, the insulating layer and the second electrode layer.

2. The traffic sensor of claim 1, wherein the substrate layer comprises PDMS.

3. The traffic sensor of claim 1, wherein the piezoelectric structure comprises a piezoelectric film.

4. The traffic sensor of claim 1, wherein the nanostructures comprise densely packed zinc oxide nanowires.

5. The traffic sensor of claim 1, wherein the insulating layer comprises a material selected from a group consisting of: PMMA, Al_2O_3 , HfO_2 , an insulating polymer and combinations thereof.

6. The traffic sensor of claim 1, wherein the first electrode layer comprises indium tin oxide.

7. The traffic sensor of claim 1, wherein the first electrode layer comprises a metal.

8. The traffic sensor of claim 1, wherein the second electrode layer comprises indium tin oxide.

9. The traffic sensor of claim 1, wherein the second electrode layer comprises a metal.

10. The traffic sensor of claim 1, wherein the packaging layer comprises PMMA.

11. A method of sensing a traffic parameter, comprising the steps of:

- (a) applying a piezoelectric nanostructure-based traffic sensor to a roadway, wherein the traffic sensor comprises:
 - (i) a PDMS flexible substrate having a top surface;
 - (ii) a piezoelectric structure, that includes a dense plurality of vertically-aligned piezoelectric elongated nanostructures, extending from the first electrode layer, the piezoelectric structure having a top end;
 - (iii) an insulating layer infused into a portion of the piezoelectric structure at the top end of the piezoelectric structure;
 - (iv) a first electrode layer disposed below the flexible substrate;
 - (v) a second electrode layer disposed on top of the insulating layer so that the insulating layer electrically isolates the second electrode layer from the top end of the piezoelectric structure; and
 - (vi) a packaging layer disposed around the substrate, the first electrode layer, the piezoelectric structure, the insulating layer and the second electrode layer;
- (b) detecting an electrical event generated by the piezoelectric nanostructure-based traffic sensor in response to a vehicle interacting with the piezoelectric nanostructure-based traffic sensor; and
- (c) correlating the electrical event with the traffic parameter.

12. The method of claim 11, wherein the traffic parameter comprises speed of the vehicle and wherein the electrical event comprises an amount of time between two different voltage maxima generated by the traffic sensor.

13. The method of claim 11, wherein the traffic parameter comprises weight of the vehicle and wherein the electrical event comprises a voltage level generated by the traffic sensor.

14. The method of claim 11, wherein the nanostructures comprise densely packed zinc oxide nanowires.

15. The method of claim 11, wherein the insulating layer comprises a material selected from a group consisting of: PMMA, Al_2O_3 , HfO_2 , an insulating polymer and combinations thereof.

16. The method of claim 11, wherein the first electrode layer and the second electrode layer each comprise a material selected from a group consisting of: indium tin oxide and a metal.

* * * * *